



## ► DPF 5200

### Printable Cast Etched Glass Film

Available in 3 finishes, DPF 5200 Etched Glass is a premium decorative, 2-mil (50 micron) printable cast vinyl designed to simulate an etched glass or sandblasted look on a variety of surfaces. Etched glass vinyl is ideal for interior and exterior applications on windows, mirrors, partitions and displays. Use it whenever you need the added elegance of an etched glass look without costly etching or sandblasting. This versatile product has been designed to deliver outstanding performance and high-quality printability. A special adhesive system ensures superior adhesion under the most demanding conditions. DPF 5200 is rated for outdoor durability up to 7 years (unprinted).

### APPLICATIONS & FEATURES

- Lay-flat liner.
- Finely balanced adhesion, tack and shrinkage properties.
- Outstanding durability, superior cutting and weeding for improved productivity.
- Ideal for interior and exterior applications on windows, mirrors, partitions and displays.
- Compatible with Eco-Solvent, Solvent, Latex and UV print systems.

### PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Gloss Meter 60° Reflection	4 to 20 Gloss Units	
THICKNESS	Micrometer, Federal Bench Type	2-mil (50 micron)	
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 4.5 lb/in	≥ 0.8 kg/cm
ELONGATION	Instron Tensile Tester as above	≥ 150%	
SHELF LIFE (IN BOX)	Ideal storage temperature 70°F (21°C) and 50% relative humidity	2 years from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	60°F to 90°F	10°C to 30°C
SERVICE TEMPERATURE RANGE	Applied to etched aluminum panels 24 hours prior to testing. 100% relative humidity 100° (38°) for 500 hours	-40°F to 200°F	-40°C to 93°C
DIMENSIONAL STABILITY	158°F (70°C), 48 hours aging	1-mil to 2-mil	0.25 mm to 0.50 mm
PEEL ADHESION	PSTC-1, 15 min, 70°F (21°C)	3.6 lb/in	0.65 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760cm/min)	150 g/2 in	30 g/cm

Standard Terms & Conditions Apply

NOTE: DPF 5200 has the following light transmission: Etched Glass: 93%, Silver Etched Glass: 70%, Sparkle Etched Glass: 82%





## TERMS & CONDITIONS

*The following is made in lieu of all warranties expressed or implied:*

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

December 2018

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA  
EUROPE:  North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands

 800 232 7161/+1 714 985 6300  800 329 2756  
 +31 70 354 4311  +31 70 355 7721

arlon.com